

Industrial Metals

Typical Chemical Composition Percent Maximum Unless Otherwise Shown

Type Number	UNS Number	C	Mn	P	S	Si	Cr	Ni	Mo	Other Elements
303	S30300	.15	2.0	.200	.15 Min.	1.0	17.00/ 19.00	8.00/ 10.00	0.60* —	— —
304	S30400	.08	2.0	.045	.030	1.0	18.00/ 20.00	8.00/ 10.50	— —	— —
304L	S30403	.03	2.0	.045	.030	1.0	18.00/ 20.00	8.00/ 12.00	— —	— —
304D	S30430	.08	2.0	.045	.030	1.0	17.00/ 19.00	8.00/ 10.00	— —	2 —
316	S31600	.08	2.0	.045	.030	1.0	16.00/ 18.00	10.00/ 14.00	2.00/ 3.00	— —
316L	S31603	.03	2.0	.045	.030	1.0	16.00/ 18.00	10.00/ 14.00	2.00/ 3.00	— —
317L	S31703	.03	2.0	.045	.030	1.0	18.00 20.00	11.00/ 15.00	3.00/ 4.00	— —